

N1020 B SR CDF

Technical data according to EN 410 and EN 673

4 mm single

4 / 16 / 4 mm double

Corrected emissivity of uncoated glass surface

0.837

Solar Energy Transmission, τ_e	12 %	11 %
Solar Energy Reflection, ρ_e	44 %	38 %
Solar Energy Absorption, a_e	43 %	51 %

Visible Light Transmission, τ_V	20 %	18 %
Visible Light Reflection (External) , ρ_{Ve}	37 %	38 %
Visible Light Reflection (Internal) , ρ_{Vi}	35 %	35 %

Ultraviolet Transmission, τ_{UV}	< 1 %
Ultraviolet Rejection	> 99 %

g value	0.22	0.35
Shading Coefficient	0.25	0.40
Total Solar Energy Rejected	78 %	65 %
Glare Reduction	78 %	79 %

U value, single glazing (W/m ² .K)	5.3	-
U value, double glazing, Air filled (W/m ² .K)	-	2.6

Emissivity, ϵ_n	0.70
--------------------------	------

Thickness without liner	45 μ
-------------------------	----------

Film Colour / Appearance	Neutral Bronze
Installation position	Interior
Warranty	7 years**

Installation Notes: X-100 must not be used to install this film. Use Film On for installation.

* Please check the complete Film to Glass Thermal Stress Compatibility Guidelines **before** film installation. ** Contact Solutia Performance Films for full details. All values for engineering parameters are determined by the manufacturer and independent testing laboratories.

N1020 B SR CDF

Features & Benefits

- Solar control and privacy film, neutral bronze appearance
- Significant improvement of working conditions due to a high reduction in solar heat gain
- Reduction in air-conditioning costs and hence a reduction in energy costs
- Daylight privacy – ‘one way’ mirror
- Excellent glare reduction
- Excellent anti-UV protection integral to the polyester: helps to reduce fading of textiles, furniture, and works of art
- Scratch resistant coating: Excellent resistance to scratching and abrasion, increasing longevity and allowing easy cleaning
- Interior installation

N1020 B SR CDF Spectra

